
01 / PRODUCT & CONSTRUCTION

PINKCITY SOLAR EPE SHEET

Multilayer encapsulation for P-type and N-type bifacial PV modules, including MonoPERC and TOPCon architectures.

SOLAR MODULE LAYERS



EVA outer layer · 30%

POE core · 40%

EVA outer layer · 30%

Construction ratios as stated in the supplied Pinkcity specification.

EVA outer layers support optical transmission and bonding; the POE core supports moisture resistance and module durability. Designed for front and rear encapsulation in compatible module constructions.

Supply formats

Nominal mass	Nominal thickness	Roll length
440 ± 20 g/m²	0.550 ± 0.10 mm	350 m
460 ± 20 g/m²	0.550 ± 0.10 mm	350 m
480 ± 20 g/m²	0.60 ± 0.10 mm	300 m
500 ± 20 g/m²	0.65 ± 0.10 mm	250 m

Width tolerance: +7 / −0 mm. Apparent thickness depends on embossing. Customer-specific width and supply formats are subject to technical agreement.

PINKCITY SOLAR FILMS (INDIA) PRIVATE LIMITED

AD Industrial Society, HARSOOLIYA, Diggi-Malpura Road, Behind Ratan Industrial Area
TEHSIL: MADHORAJPURA, DIST. : JAIPUR, PIN : 303904

info@pinkcitysolarfilms.com | www.pinkcitysolarfilms.com

02 / MATERIAL PERFORMANCE

Technical specifications

Product values and test methods reproduced from the supplied Pinkcity technical data sheet.

Property	Specification	Method
Thickness	450–700 µm (±5%)	ASTM D6988-13
Mass per unit area	390–580 g/m² (±5%)	Weighing balance
Width	Custom (+7 / −0 mm)	Scale
Gel content	≥75%	ASTM D2765
Thermal shrinkage / MD	≤3%	150°C oven / 5 min
Thermal shrinkage / TD	≤2%	150°C oven / 5 min
UV cut-off wavelength	360 nm	IEC 62788-1-4
Optical transmission / 190–1100 nm	≥91%	IEC 62788-1-4
UV transmission / 290–380 nm	≥80%	IEC 62788-1-4
Dielectric strength	>20 kV/mm	ASTM D149
Glass adhesion	≥60 N/cm	ASTM D903
Tensile strength / MD & TD	≥10 MPa	ASTM D882
Elongation	≥500%	ASTM D882
Volume resistivity	≥1 × 10^{15} Ω·cm	ASTM D257
Comparative tracking index	600 V	IEC 60112:2003

MD: machine direction. TD: transverse direction. Overall thickness and GSM ranges are distinct from the nominal roll categories on page 1. Confirm the ordered grade and acceptance tolerances before procurement.

03 / PROCESS & QUALIFICATION

From film to module

Lamination guidance, handling recommendations and product qualification notes.

Lamination starting window

Parameter	Single chamber	Double / first	Double / second
Actual hot-plate temperature	143–155°C	120–135°C	145–155°C
Vacuum duration	330–390 s	400–480 s	30–60 s

The temperature and vacuum windows above are from the Pinkcity sheet. Tune the process to the laminator, film grade and module bill of materials (BOM). Prepare gel-content samples using the actual module layer stack; validate cure, adhesion and appearance before production.

Handling & storage recommendations

Store indoors at 0–30°C and below 60% relative humidity, protected from direct sunlight, heat and dust. Keep rolls in their original packaging until use. Use the film within 8 hours after opening. Recommended shelf life: 5 months from the date of manufacture under the specified storage conditions.

Performance & certification information

The supplied Pinkcity sheet describes PID resistance, UV and weather resistance, sustained adhesion, ease of lamination and damp-heat resistance up to 3,000 hours. Detailed test conditions and results should be obtained for the selected film grade and module BOM.

Certification reference in the supplied Pinkcity sheet:
UL certificate number: E552145
Report reference: E552145-20260327
Confirm certificate holder, covered grade and current scope against the certificate before using a certification claim.

Technical agreement

Specifications describe the supplied product information and do not replace a purchase specification or module qualification. Confirm optical measurement bands, ordered dimensions, tolerances, shelf life and approved lamination settings with Pinkcity. Performance depends on the full module construction and processing conditions.

PSF / EPE / TDS • Issue: 04 October 2026

PINKCITY SOLAR FILMS (INDIA) PRIVATE LIMITED

AD Industrial Society, HARSOOLIYA, Diggi-Malpura Road, Behind Ratan Industrial Area
TEHSIL: MADHORAJPURA, DIST. : JAIPUR, PIN : 303904

info@pinkcitysolarfilms.com | www.pinkcitysolarfilms.com